



UNIVERSITÀ  
DEGLI STUDI  
FIRENZE

## FLORE

# Repository istituzionale dell'Università degli Studi di Firenze

### **Effect of steam saturated atmosphere on some physical and mechanical properties of poplar wood**

Questa è la Versione finale referata (Post print/Accepted manuscript) della seguente pubblicazione:

*Original Citation:*

Effect of steam saturated atmosphere on some physical and mechanical properties of poplar wood / Lorenzo Barnini; Giacomo Goli; Marco Fioravanti. - STAMPA. - (2014), pp. 14-15. ( Final Cost Action FP0904 Conference "Recent Advances in the Field of TH and THM Wood Treatment" Skellefteå, Sweden 19-21 May 2014).

*Availability:*

The webpage <https://hdl.handle.net/2158/957936> of the repository was last updated on 2016-11-14T17:54:49Z

*Publisher:*

Luleå University of Technology

*Terms of use:*


Open Access

La pubblicazione è resa disponibile sotto le norme e i termini della licenza di deposito, secondo quanto stabilito dalla Policy per l'accesso aperto dell'Università degli Studi di Firenze (<https://www.sba.unifi.it/upload/policy-oa-2016-1.pdf>)

*Publisher copyright claim:*

La data sopra indicata si riferisce all'ultimo aggiornamento della scheda del Repository FloRe - The above-mentioned date refers to the last update of the record in the Institutional Repository FloRe

(Article begins on next page)



**Luleå University of Technology**  
 Division of Wood Science and Engineering  
 Forskargatan 1  
 931 87 Skellefteå

ISBN 978-91-7439-937-0 (print)  
 ISBN 978-91-7439-938-7 (pdf)



Final Cost Action FP0904 Conference  
**“Recent Advances in the Field of TH and THM Wood Treatment”**  
 May 19-21, 2014, Skellefteå, Sweden

# LULEÅ UNIVERSITY OF TECHNOLOGY

Book of Abstracts

Organized By:

- Luleå University of Technology, Skellefteå,
- Division of Wood Technology and
- COST Action FP0904  
[www.cost-fp0904.ahb.bfh.ch](http://www.cost-fp0904.ahb.bfh.ch)



**itu.se**



Book of abstracts includes the scientific program and the abstracts of papers will be presented at the Final COST Action FP0904 Conference on “**Recent Advances in the Field of TH and THM Wood Treatment**” at the **Luleå University of Technology**, Division of Wood Science and Engineering, in Skellefteå, Sweden on 19–21 May 2014.

The main objective of COST Action FP0904 is to achieve a better understanding on mechanical and chemical transformations of wood during Thermo-Hydrous (TH)/ Thermo-Hydro-Mechanical (THM) processing through collaborations between different researchers from the wood and material sciences. This Action provides cooperation and encourages research between research groups from academia and industry to help to overcome the challenges in scaling-up research findings, improving full industrial production, process improvement, in understanding the relations between the processing parameters, material properties and the development of new products. The COST Action FP0904 consists of three Working Groups (WGs):

WG1: Identification of chemical degradation of wood under Thermo- Hydrous treatment

WG2: Modelling of Thermo-Hydro-Mechanical behaviour of wood during processing

WG3: Innovation and new products by Thermo-Hydro-Mechanical processing

We wish the conference provides a forum and an opportunity for experts and young researchers from worldwide academia and industry to present their latest research, exchanging and developing new ideas within the field of TH and THM wood treatment. The objectives of this conference are to present and discuss the state-of-the-art of TH/THM wood treatment in open and closed systems and the challenges in wood characterization and scaling-up from laboratory to full industrial production, through a discussion of the latest research results and new ideas. The key objective of this Final Action FP0904 Conference is to present the main results of the Action, to summarise the scientific progress achieved and to formulate open questions and further challenges. This conference will include an evaluation session with representatives of COST and Action Management Committee members.

Luleå University of Technology (LTU), established in 1971, is the northernmost University of Technology in Scandinavia and is known for its education and research within the field Wood Science and Engineering. The research area of Wood Technology, Wood Physics and Wood Products Engineering is since 1982 established in the city of Skellefteå. Northern Sweden is one of the most important areas in Europe when it comes to forestry and the wood industry. The Wood Science and Engineering group at LTU are engaged in a wide range of fields within the entire chain from forest to finished product.

On behalf of the COST Action FP0904 Management Committee I would like to thank everybody that kindly contributed to this meeting: all the authors and specially the keynote speakers; Callum Hill, Eiichi Obataya, Otto Th. Eggert and Kevin Candelier.

I gratefully acknowledge the help of the Scientific Advisory Committee in reviewing the abstracts and preparing the scientific program.

I express my sincere gratitude to Dick Sandberg and Mojgan Vasiri for their works in preparing the “book of abstracts” and also as the local organizer.

Parviz Navi

Chair of COST Action FP0904

### **Scientific Advisory Committee**

Parviz Navi	Bern University of Applied Sciences, Switzerland
Dennis Jones	SP Technical Research Institute of Sweden
George Jeronimidis	Reading University, United Kingdom
Mark Hughes	Aalto University, Finland
Mathieu Petrissans	University Nancy 2, France
Lennart Salmen	Innventia Stockholm, Sweden
Joseph Gril	University Montpellier 2, France
Peer Haller	Technische Universität Dresden, Germany
Dick Sandberg	Luleå University of Technology, Skellefteå, Sweden
Mojgan Vaziri	Luleå University of Technology, Skellefteå, Sweden
Dr Christelle Ganne-Chedeville	Bern University of Applied Sciences, Switzerland

### **Local Organisation**

Dick Sandberg	LTU Skellefteå
Mojgan Vaziri	LTU Skellefteå

### **Web-page administration**

Mojgan Vaziri	LTU Skellefteå
Ted Karlsson	Editor-In-Chief , LTU

### **Accounting & Administration**

Fredrik Degerman	Economist, LTU Skellefteå
Eva-Stina Nordlund	Institute's administrator, LTU Skellefteå
Cristoffer Schutze	Project administrator

### **Registrarion**

Mrs Inger Lindbäck	NEX meeting & event
--------------------	---------------------

<b>DATE</b>	<b>18-21 MAY</b>
<b>VENUE</b>	Arenan at Campus Skellefteå
<b>OFFICIAL LANGUAGE</b>	The official conference language will be English.
<b>BADGE</b>	<p>Delegates must report to the registration desk to collect their name badges and conference materials. Every participant including his/her accompanying person is requested to wear a name badge during the conference period.</p> <p>Venue : Lobby Arenan The desk will also be operating during the following schedule</p>
<b>REGISTRATION</b>	18 May Sunday 14:00-16:30
<b>RECEPTION DESK</b>	<p>18 May Sunday 14:00-16:30 19 May Monday 07:20-11:30 20 May Tuesday 08:00-08:40 21 May Wednesday 07:30-11:00</p>
<b>SPEAKER'S RECEPTION DESK</b>	<p>Regarding Oral Presentations, please note that: It is expected that all presentations will be presented in English using Microsoft PowerPoint with a common computer provided by the conference organizers. We encourage you to check your PowerPoint file compatibility in advance. An overhead projector will be available by special request.</p> <p><b>IMPORTANT!</b> All speakers are required to check in at the Speaker's Reception Desk by 18 &amp; 19 May in order to hand over the CD or USB with the PowerPoint file, to be downloaded on the conference computer. All speakers during Tuesday <b>must</b> hand in their presentations during Monday May 19. The opening times for the Speaker's Reception Desk are the same as for the Information Desk, Sunday 14:00-16:30 and Monday 7:20-11:30.</p> <p>During Tuesday and Wednesday only by request in advance, (please contact the General Information Desk for further assistance)</p>

Time	SUNDAY MAY 18	Time	MONDAY MAY 19	Time	TUESDAY MAY 20	Time	WEDNESDAY MAY 21
		07:20-08:20	Registration	09:00-9:30	<b>Session 3:</b> New products by THM-open system <b>Keynote 3:</b> Otto Th. Eggert	08:00-08:30	Coffee
		08:20-08:40	Opening session	09:30-10:30	3 Full Oral Presentations	08:30-10:30	Management Committee Meeting and the Evaluation Panel (Closed session)
		08:40-09:20	<b>Session 1:</b> Chemical degradation of wood under thermo-hydrous treatments <b>Keynote 1:</b> Callum Hill	10:30-11:00	Coffee Break		
		09:20-10:00	2 Full Oral Presentations	11:00-11:40	2 Full Oral Presentations		
		10:00-10:30	Coffee Break	11:40-12:00	5 Poster Presentations		
		10:30-11:10	2 Full Oral Presentations	12:00-13:30	Lunch		
		11:10-11:30	6 Poster Presentations	13:30-14:10	<b>Session 4:</b> Innovations and new products laboratory and industrial scale & STSM presentations <b>Keynote 4:</b> Kévin Candelier		
		11:30-13:00	Lunch	14:10-15:10	3 Full Oral Presentations		
		13:00-13:40	<b>Session 2:</b> Modeling of THM processing and predicting the behavior of THM <b>Keynote 2:</b> Eiichi Obataya	15:10-15:40	Coffee Break		
		13:40-14:20	2 Full Oral Presentations	15:40-17:18	8 Oral Presentations & 2 Poster Presentations		
		14:20-14:50	Coffee Break	19:00-22:00	Conference Dinner		
14:00-18:30	Registration And Welcome Reception	14:50-15:50	3 Full Oral Presentations				
		15:50-16:13	7 Poster Presentations				
		16:15-18:00	Posters & Visit To LTU Laboratory				

## Programme

SUNDAY MAY 18 <sup>TH</sup>	
14:00-18:30	<b>Registration And Welcome Reception</b>
MONDAY MAY 19 <sup>TH</sup>	
07:20-08:20	<b>Registration At the Desk (Conference Place)</b>
08:20-08:40	<b>Opening Session</b>
08:40-09:20	<b>Session 1: Chemical degradation of wood under thermo-hydrous treatments</b> Chairperson: Mark Hughes Keynote 1: <b>Callum Hill</b> , Thermally Modified Wood – the role of hemicelluloses, <b>p. 1</b>
09:20-09:40	Full O.pres 1:1 <u>Wim Willems</u> <b>Characterisation of thermally modified wood by a novel means of moisture sorption isotherm analysis, p. 3</b>
09:40-10:00	Full O.pres 1:2 <u>Wieslaw Olek</u> , Patrick Perré, Jerzy Weres, Romain Rémond <b>Water diffusivity of thermally modified beech wood, p. 5</b>
10:00-10:30	<b>Coffee Break</b>
10:30-10:50	Full O.pres 1:3 <u>Michael Altgen</u> , Jukka Ala-Viikari, Timo Tetri, Antti Hukka, Holger Militz <b>The impact of elevated steam pressure during the thermal modification of Scots pine and Norway spruce, p. 7</b>
10:50-11:10	Full O.pres 1:4 Iris Brémaud, <u>Sandrine Bardet</u> , Joseph Gril, Patrick Perré <b>Effects of water re-saturation conditions and associated extractives leaching on thermal softening of wet wood, p. 8</b>
11:10-11:30	<b>Poster Session</b>
11:12-11:15	Poster 1:1 <u>Lukas Brösel</u> , Lothar Clauder, <u>Alexander Pfriem</u> <b>Flammability tests on thermally modified and untreated timbers, p. 10</b>
11:15-11:18	Poster 1:2 Mohamed Tahar Elaieb, <u>Kevin Candelier</u> , Anélie Petrissans, Stéphane Dumarcay, Philip Gerardin, Mathieu Petrissans <b>Chemical modification during heat treatment of Tunisian soft wood species, p. 12</b>
11:18-11:21	Poster 1:3 <u>Lorenzo Barnini</u> , <u>Giacomo Goli</u> , Marco Fioravanti <b>Effect of steam saturated atmosphere on some physical and mechanical properties of poplar wood, p. 14</b>
11:21-11:24	Poster 1:4 <u>Olov Karlsson</u> , Ola Dagbro, Kurt Granlund <b>Soluble degradation products in thermally modified wood, p. 16</b>
11:24-11:27	Poster 1:5 <u>Maria-Cristina Popescu</u> , Carmen-Mihaela Popescu <b>An NIR and XPS study of the lime wood samples modified for different periods at lower temperature and relative humidity, p. 18</b>
11:27-11:30	Poster 1:6 M. Hakki Alma, Eyyup Karaogula, <u>Tufan Salanb</u> , Nasir Narlioglua, H. İbrahim Şahinc, Cengiz Güler <b>Effect of thermal treatment on XRD, ATR-FTIR AND SEM analysis of several wood species, p. 20</b>
11:30-13:00	<b>Lunch</b>

## Programme

13:00-13:40	<b>Session 2: Modeling of THM processing and predicting the behavior of THM</b> Chairperson: Joseph Gril Keynote 2: <b>Eiichi Obataya</b> , Recoverable effects of heat treatment, <b>p. 21</b>
13:40-14:00	Full O.pres 2:1 Sung-Lam Nguyen, Omar Saifouni, <u>Jean-François Destrebecq</u> , Rostand Moutou Pitti <b>An incremental model for wood behaviour including hydro-lock effect, p. 24</b>
14:00-14:20	Full O.pres 2:2 <u>Andreja Kutnar</u> , Frederick A. Kamke, William Gacitúa <b>Elastic cell wall modulus and hardness of S2 layer and middle lamella in viscoelastic thermal compressed wood, 26</b>
14:20-14:50	<b>Coffee Break</b>
14:50-15:10	Full O.pres 2:3 Giacomo Goli, <u>Bertrand Marcon</u> , Marco Fioravanti <b>Wood heat treatment modifications: effects of initial moisture and air exchange rate on kinetic and final product characteristics, p. 28</b>
15:10-15:30	Full O.pres 2:4 <b>35</b> Patrick PERRE, <u>Romain REMOND</u> <b>A comprehensive dual-scale computational model able to simulate the heat-treatment of a thick-bed of particles or boards, p. 30</b>
15:30-15:50	Full O.pres 2:5 Hassen Riahi, Rostand Moutou Pitti, <u>Frédéric Dubois</u> <b>Numerical analysis of timber fracture due to mechanical and thermal loads: an approach based on invariant integral A, p. 32</b>
15:50-16:13	<b>Poster Session</b>
15:52-15:55	Poster 2:1 Hassen Riahi, <u>Rostand Moutou Pitti</u> , Alaa Chateauneuf, Frédéric Dubois <b>Stochastic analysis of mixed mode fracture in timber material using polynomial chaos expansion, p. 34</b>
15:55-15:58	Poster 2:2 Dang Djily, <u>Rostand Moutou Pitti</u> , Evelyne Toussaint, Michel Grédiac <b>Experimental evidence of water diffusion gradient in wood using the grid method, p. 36</b>
15:58-16:01	Poster 2:3 <u>Emilia-Adela Salca</u> , Salim Hiziroglu <b>Evaluation of roughness and hardness of heat treated wood species, p. 38</b>
16:01-16:04	Poster 2:4 <u>Bogdan Bedeleian</u> , Daniela Sova <b>Influence of air parameters on drying time and energy consumption during thermo-hydro processing of wood, p. 40</b>
16:04-16:07	Poster 2:5 <u>Alexey Vorobyev</u> , Nico van Dijk, Ingela Bjurhager, E. Kristofer Gamstedt <b>Determination of elastic behaviour of precious samples from large wooden structures of cultural heritage including screening potential in process treatment, p. 42</b>
16:07-16:10	Poster 2:6 <u>Cécilia Gauvin</u> , Kaoru Endo, Delphine Jullien, Eiichi Obataya, Joseph Gril <b>Effect of hygrothermal treatments on the physical properties of wood, p. 43</b>
16:10-16:13	Poster 2:7 Mojgan Vaziri, <u>Sven Berg</u> , Dick Sandberg <b>Three-dimensional finite element modelling of heat transfer for linear friction welding of Scots pine, 45</b>
16:15-18:00	<b>Posters &amp; Visit To LTU Laboratory</b>

**Programme**

TUESDAY MAY 20 <sup>TH</sup>	
9:00-9:30	<b>Session 3:</b> Innovation and new products in THM treatments Chairperson: Peer Haller Keynote 3: <b>Otto Th. Eggert</b> , Solid wood bending – a stunning production system, p. 47
9:30-9:50	Full O.pres 3:1 <u>Jörg Wehsener</u> , Jens Hartig, <u>Peer Haller</u> <b>Investigations on the recovery behaviour of beech (<i>Fagus sylvatica</i>) wood densified transverse to the grain, p. 48</b>
9:50-10:10	Full O.pres 3:2 <u>Lars Blomqvist</u> , Jimmy Johansson, Dick Sandberg <b>Modification of surface veneer to reduce damage in laminated veneer products during manufacturing, p. 50</b>
10:10-10:30	Full O.pres 3:3 <u>Róbert Németh</u> , József Ábrahám, Mátyás Báder <b>Effect of high temperature treatment on selected properties of beech, hornbeam and turkey oak wood, p. 52</b>
10:30-11:00	Coffee Break
11:00-11:20	Full O.pres 3:4 <u>Alexander Pfriem</u> <b>Thermally modified wood for use in musical instruments – a review, p. 54</b>
11:20-11:40	Full O.pres 3:5 <u>Nozomi Takemura</u> , Aoi Hirano, Eiichi Obataya, Koji Adachi <b>Compressive elasticity of compressed wood and its application to flexible wooden beam, p. 56</b>
11:40-12:00	Poster Session
11:42-11:45	Poster 3:1 <u>Aleš Straže</u> , Miljenko Klarić, <u>Stjepan Pervan</u> , Silvana Prekrat, Željko Gorišek <b>Accelerated artificial ageing of thermally treated ash wood, p. 58</b>
11:45-11:48	Poster 3:2 <u>Lothar Clauder</u> , Alexander Pfriem <b>Comparative durability tests on TMT Beech – preliminary results, p. 60</b>
11:48-11:51	Poster 3:3 <u>Veikko Möttönen</u> , Juhani Marttila, Jukka Antikainen, Henrik Heräjärvi, Erkki Verkasalo <b>Colour, MOE and MOR of silver birch and European aspen wood after compression and thermal modification in an industrial scale modification chamber, p. 62</b>
11:51-11:54	Poster 3:4 <u>Ali Akbar Enayati</u> , Fatemeh Taheri, Razieh Mosayyebi <b>Effect of heat treatment conditions(Heat-temperature and Initial (Moisture Content )on the pH value and buffer capacity of Poplar Wood (<i>Populus alba</i>), p. 63</b>
11:54-11:57	Poster 3:5 <u>Marek Grzeńkiewicz</u> <b>Effect of thermal modification of beech wood on its MOE and other mechanical properties, p. 65</b>
12:00-13:30	Lunch

## Programme

13:30-14:10	<p><b>Session 4:</b> Environmental impact assessment of THM products &amp; STSM presentations Chairperson: Andreja Kutnar Keynote 4: <b>Kévin Candelier</b>, Characterization of physical and chemical changes occurring during wood thermal degradation. Influence of treatment intensity, wood species and inert atmosphere, <b>p. 67</b></p>
14:10-14:30	<p>Full O.pres 4:1 <u>Michael Burnard</u>, Andreja Kutnar <b>Restorative environmental design: A design paradigm for thermally modified wood, p. 70</b></p>
14:30-14:50	<p>Full O.pres 4:2 <u>José Sánchez del Pulgar</u>, Illaria Santoni, Luca Cappellin, Anrea Romano, Cuccui Ignazia, Franco Biasioli, Ottaviano Allegretti <b>Rapid assessment by PTR-ToF-MS of the effect on volatile compound emission of different heat treatments on larch and spruce, p. 72</b></p>
14:50-15:10	<p>Full O.pres 4:3 <u>Carmen-Mihaela Popescu</u>, Maria-Cristina Popescu, Petronela Gradinariu <b>Soft and white rot degradation resistance of thermo-hydro-mechanical processed hardwood evaluated by infrared spectroscopy, p. 74</b></p>
15:10-15:40	<b>Coffee Break</b>
15:40-16:00	<p>Full O.pres 4:4 <u>Ekaterina Sidorova</u>, Sheikh A. Ahmed, Diego Elustondo <b>Wood thermal-modification at Luleå University of Technology, p. 76</b></p>
16:00-16:10	<p>Short O.pres 4:5 <u>Carmen Cristescu</u>, Dick Sandberg <b>Self-bonding of veneers with heat and pressure– a full scale test, p. 77</b></p>
16:10-16:20	<p>Short O.pres 4:6 <u>Nebojša Todorović</u>, Goran Milić, Zdravko Popović <b>Estimation of heat-treated beech wood properties by FT-NIR spectroscopy: effect of radial and cross sectional surface, p. 78</b></p>
16:20-15:50	<b>Poster Session/STSM Presentation Session</b>
16:22-16:25	<p>Poster 4:1 <u>Jonaz Nilsson</u>, Jimmy Johansson, Dick Sandberg <b>Densified and thermally modified wood as outer layers in light-weight panels for furniture and joinery, p. 80</b></p>
16:25-16:28	<p>Poster 4:2 <u>Sandak Jakub</u>, Riggio Mariapaola, Pauliny Dusan, Sandak Anna <b>Densified wood as a resource for novel nail-like connectors, p. 82</b></p>
16:28-16:38	<p>Short O.pres 5:1 <u>Wim Willems</u>, Joël Hamada, Mathieu Pétrissans, Philippe Gérardin, <b>Characterization of thermally modified wood by oxygen bomb calorimetry, p. 84</b></p>
16:38-16:48	<p>Short O.pres 5:2 <u>Mirko Kariz</u>, Manja Kitek Kuzman, Milan Sernek, Mark Hughes, Lauri Rautkari, Frederick A. Kamke, Andreja Kutnar <b>Influence of temperature of thermal modification on compressive densification of spruce, p. 86</b></p>
16:48-16:58	<p>Short O.pres 5:3 <u>Lothar Clauder</u>, Alexander Pfriem, Maria Rådemar, Lars Rosell, Marcus Vestergren <b>Emissions from TMT products, p. 88</b></p>

## Programme

16:58-17:08	Short O.pres 5:4 <u>Kristiina Laine</u> , Lauri Rautkari, Mark Hughes, Kristoffer Segerholm, Magnus Wålinder <b>Set-recovery and micromorphology of surface densified wood, p. 90</b>
17:08-17:18	Short O.pres 5:5 <u>Susanna Källbom</u> , Lauri Rautkari, Magnus Wålinder, Dennis Jones, Kristoffer Segerholm <b>Water vapour sorption properties and surface chemical analysis of thermally modified wood particles, p. 92</b>
19:00-22:00	Conference Dinner

WEDNESDAY MAY 21 <sup>TH</sup>	
08:00-08:30	Coffee
8:30-10:30	Management committee meeting with the COST representative and the evaluation panel (Closed Session)

Sandberg D. and Vaziri M. (Eds.)

# Abstracts

# Effect of steam saturated atmosphere on some physical and mechanical properties of poplar wood

Lorenzo Barnini, Giacomo Goli, Marco Fioravanti

Dipartimento di Gestione dei Sistemi Agrari, Alimentari e Forestali (GESAAF), Università di Firenze, Via S. Bonaventura 13, 50145 Firenze, Italy

marco.fioravanti@unifi.it

**Keywords:** thermal treatment, saturated steam

Poplar wood is a specie that is and it was widely used in Italy as solid timber or, more recently, as a part of wood-engineered products. Many important Italian heritage objects (e.g. panel paintings, wooden sculptures, old timber structures) were made in poplar. According to recent studies [1], now days the yearly need of poplar wood in Italy is around  $3.9 \cdot 10^6$  m<sup>3</sup> from whom about one half are home grown.

Because poplar wood is very suitable for applications where the lightness is essential such as for the caravan sector, where the wood durability is essential as well, a research was planned in order to understand 1) the effects of the hydro-thermal (HT) treatment on modification of some poplar wood properties, and 2) for studying the suitability of HT as a means for producing artificial accelerated ageing of wood to be used in the restoration of wooden Cultural Heritage.

In this work, the effect of HT treatments in saturated moisture conditions is studied and the treatments was performed according to the experimental protocol presented in Table 1.

Table 1. Experimental matrix and main results in terms of colour variation ( $\Delta E$ ), mass variation ( $\Delta MASS$ ), MOE variation ( $\Delta MOE$ ) and moisture content variation ( $\Delta MC$ ) at standard environmental conditions (20°C and 65% RH) after hydro thermal treatment in saturated vapour conditions for the given temperatures and treatment periods

	1h	2h	3h	6h	12h
100°C			4,90 -0,9% 2,2% -0,47%	5,72 -1,3% -0,4% -0,49%	
120°C			8,30 -1,6% 2,1% -1,01%	11,15 -2,2% 1,3% -0,96%	15,62 -2,3% 3,4% -0,97%
140°C		15,27 -2,9% 4,7% -1,30%	17,04 -3,6% 9,4% -1,40%	21,96 -4,5% 2,3% -2,11%	
150°C	17,00 -3,4% 7,4% -1,59%		28,83 -7,4% -5,7% -3,43%		$\Delta E$ $\Delta MASS$ $\Delta MOE$ $\Delta MC$

Different samples of poplar wood (*Populus x euroamericana* Guinier) were prepared from the same board after a first cut by cleavage. The properties variations were determined as the difference between the treated and untreated state (20°C and 65% RH) and referred to the untreated state. The properties variations were studied on: colour, mass, MOE and moisture content. All these features, except the moisture content which is compared to a reference sample, were measured as a variation on the same specimens. The measurement of the colour was performed according to the CIE L\*a\*b\* 1976 definitions and by a Konica-Minolta mod. CM700d colorimeter. The MOE was measured by a tensile test on small samples (8x3x150 mm) up to a 30% of ultimate load. Qualitative chemical analyses of the samples were performed by FTIR after extraction in Soxhlet as from the method defined by [3]. In Figure 1 is reported the mass variation for different temperatures and periods of treatment.




Figure 1. Mass variation as a percentage of the initial mass vs. time for different treatment temperatures and periods

The mass losses are clearly depending on the treatment intensity and the reaction kinetics in saturated steam is very fast if compared to treatments performed for similar temperatures in conventional oven [2]. A mass loss of 8% (at 20°C and 65% RH equilibrium state) in the former case is attained after 3 hours of treatment at 150°C while in the latter after about 20 hours at 180°C. The equilibrium moisture content variation at 20°C and 65% RH result in the same trend than mass loss. The volume have shown an opposite behaviour if compare to oven treatments and result increased. The colour variations present trends in line with the mass loss. MOE show a tendency to increase up to 10% until a mass loss of 4% is attained. For larger mass losses MOE tends to reduce again getting to the same value of untreated samples at 5%. For higher mass losses MOE gets again to lower values if compared to untreated samples. From a chemical point of view results shown that a significant loss of glucoxylans starts after 6 hours of treatments at 100°C, and they completely disappear at 120°C for 12 hours, 140°C for 6 hours or 150°C for 1 hour. The other wood components do not seem to be very affected by the treatment.

#### REFERENCES

1. A. Brega, *Il Sole 24 ore*, December 28, 2011
2. G. Goli, M. Fioravanti, G. Del Bianco, *COST Action FP 0904 Thermo-Hydro-Mechanical Wood Behaviour and Processing - 26-28/03/2012 - Nancy (FR)*, 90-92, 2012
3. TAPPI T 264 cm-07, 2007

#### ACKNOWLEDGMENTS

The authors acknowledge the financial support of Toscana Regional Administration with the POR CRoO projects funding line as well as the ERDF funding line.